



RiWay-Yx

12-Hydroxy Stearic Acid (12-HSA)

Description

RiWay-Yx is made from renewable raw materials derived from plant origin. It has versatile properties that improve a product's chemistry/processability.

Characteristic Values*

Properties	Units	AOCS Test Method	<i>RiWay-Yx</i> <i>12-HSA</i>
Physical:			
Appearance	@ 25°C	Visual	Ivory Flakes/Beads
Clarity molten form	Gardner Tube	Visual	Clear
Color molten form	Gardner Scale	Visual	4 max.
Moisture	%	Ca 2c-25	0.5 max.
Melting Point	°C	Cc 1-25	72 +/- 2

*Slight variations in the characteristic values stated are possible due to production made out of natural raw materials.

Packing: In Bags (net wt. 25 kgs)

Shelf Life / Storage: Shelf life is 12 months from manufacturing date when stored in a cool place (< 35°C), in tightly closed packaging, protected from dust, heat, & moisture.

Applications

Industry: Plastics	Key Role	Benefits	Dosage %
PVC	External Lubricant	Mold Release Agent	0.3 – 1.0

The information given in this leaflet is based on our own research & development work and is correct to the best of our knowledge. We recommend that the actual users should conduct their own tests to determine the suitability of our products for their end use. Users should refer to the MSDS and other relevant data for safe handling. Our Company shall not be responsible for any loss, injury, damage, and patent or law infringement, resulting from the use of this information.