RICINASH

Renewable Materials Private Limited

202/203 Magnum Opus, Shantinagar Industrial Estate, Vakola, Santacruz (E), Mumbai 400055, Maharashtra, INDIA Tel: ++91-9820358740 Email: <u>ricinash@gmail.com</u> CIN No. U15140MH1997PTC105499

Product Spec Sheet - rev.01/11/25

RiCas-Dx

Dehydrated Castor Oil

HSN: 15180029

Description

RiCas-Dx is a drying vegetable oil made from renewable raw materials derived from plant origin. It mostly meets with bureau specifications IS 81: 1989, Grade-1.

Characteristic Values*

Properties	Units	AOCS Test Method	RiCas-Dx DCO-M
Physical:	<u>.</u>		·
Appearance	@ 25°C in Gardner Tube	Visual	Lt. Yellow Liquid
Clarity	@ 25°C in Gardner Tube	Visual	Clear Star-Shine
Color	@ 25°C in Gardner Tube	Visual	8 max
Viscosity	@ 25°C in Gardner Tube	Tq 1a-64	3 +/- 1 bubble secs (G – J Gardner Scale)
Moisture	%	Ca 2c-25	0.2 max
pH	of 10% Aqueous Extract	Litmus Paper	5.5 - 7.0
Chemical:			
Acid Value	mg KOH/g	Cd 3d-63	6 max
Saponification Value	mg KOH/g	Cd 3-25	188 - 195
Iodine Value	cg I ₂ /g	Tg 1-64	127 - 137
Hydroxyl Value	mg KOH/g	Cd 13-60	25 +/- 5

^{*}Slight variations in the characteristic values stated are possible due to production made out of natural raw materials but it shall have no influence on its application functionalities.

Packing: In Plastic Barrels (net wt. 200 kgs)

Shelf Life / Storage: Shelf life is 12 months from manufacturing date when stored in a cool place ($< 35^{\circ}$ C),

in tightly closed packaging, protected from dust, heat, & moisture.

Authorization: (sign not necessary if emailed doc.)

Approved by:	Approved by:	Approved by:
TECH: EX	MFGN: EX	MKTG: EX

The information contained in this document is based on our own research and development and is to the best of our knowledge reliable. Users should, however, conduct their own tests to determine the suitability of our products for their own specific purposes and the legal status for their intended use of the product. Statements contained herein should not be considered as a warranty of any kind, expressed or implied, and no liability is accepted for the infringement of any patents.